



ARTROM STEEL TUBES S.A.

Draganesti Str. 30, Slatina, jud. OLT, Romania 230119
 Tel: +40 (249) 436862, 434640, 434641 Fax: +40 (249) 434330, 437288
 E-mail: office.slatina@artrom.com www.artrom.com
 EUID: ROONRC.J28/9/1991; J28/9/31.01.1991 VAT No. RO 1510210/1992
 Subscribed and Paid Share Capital: 291.587.538,34 lei

Tab.3- Chemical Composition (%) acc.API 5CT

Level	Grade	Mass Fraction [%]												
		C		Mn		Mo		Cr		Ni	Cu	P	S	Si
		min	max	min	max	min	max	min	max	max	max	max	max	max
PSL1	H40											0.030	0.030	
	R95		0.45		1.90							0.030	0.030	0.45
	C110		0.35		1.20	0.25	1.00	0.40	1.50	0.99		0.020	0.005	
PSL2	J55											0.030	0.030	
	K55											0.030	0.030	
	L80(1)		0.43		1.90					0.25	0.35	0.030	0.030	0.45
	N80(1)											0.030	0.030	
	N80(Q)											0.030	0.030	
	P110											0.030	0.030	
	T95(1)		0.35		1.20	0.25	0.85	0.40	1.50	0.99		0.020	0.010	
Q125		0.35		1.35		0.85		1.50	0.99		0.020	0.010		

ARTROM STEEL TUBES S.A. Cod: FCU-01, Ed. 5 Rev. 1/2023



API:
5CT-2357
5L-1271

LRQA:
ISO 9001
ISO 14001
ISO 45001

TUV:
PED/AD-2000 W0/W4
Vd TUV

TUV CPR:
EN 10210-1,2
EN 10255

DNV
RINA

LRQA:
IATF 16949