



ARTROM STEEL TUBES S.A.

Draganesti Str. 30, Slatina, jud. OLT, Romania 230119
 Tel: +40 (249) 436862, 434640, 434641 Fax: +40 (249) 434330, 437288
 E-mail: office.slatina@artrom.com www.artrom.com
 EUID: ROONRC.J28/9/1991; J28/9/31.01.1991 VAT No. RO 1510210/1992
 Subscribed and Paid Share Capital: 291.587.538,34 lei

Tab.5 Mechanical Properties Acc.API 5CT

Level	Grade	Yield Strength (ksi)		Tensile Strength (ksi)	Total elongation under Load %	Hardness max.		Specified Wall Thickness (In.)	Allowable Hardness Variation
		minim	maxim	minim		HRC	HBW		HRC
PSL1	H40	40	80	60	0.5				
	R95	95	110	105	0.5				
	C110	110	120	115	0.7	30	286	≤0.500 0.501 la 0.749 0.750 la 0.999 ≥1.000	3.0 4.0 5.0 6.0
PSL2	J55	55	80	75	0.5				
	K55	55	80	95	0.5				
	L80(1)	80	95	95	0.5	23.0	241		
	N80(1)	80	110	100	0.5				
	N80(Q)	80	110	100	0.5				
	P110	110	140	125	0.6				
	T95(1)	95	110	105	0.5	25.4	255	≤0.500 0.501 la 0.749 0.750 la 0.999 ≥1.000	3.0 4.0 5.0 6.0
Q125	125	150	135	0.65			≤0.500 0.501 la 0.749 ≥0.750	3.0 4.0 5.0	

ARTROM STEEL TUBES S.A. Cod: FCU-01, Ed. 5 Rev. 1/2023



API:
5CT-2357
5L-1271

LRQA:
ISO 9001
ISO 14001
ISO 45001

TUV:
PED/AD-2000 W0/W4
Vd TUV

TUV CPR:
EN 10210-1,2
EN 10255

DNV
RINA

LRQA:
IATF 16949