





Tab 1.1 Mechanical tubes made in Workshop no.2 CPE ARTROM STEEL TUBES

Cost categories/sizes of tubes rolled in Workshop no.2 CPE

WT	mm	2.3	2.6	2.77	2.87	2.9	3.2	3.6	3.91	4	4.5	5	5.5	6.02	6.3	7.1	7.62	8.0	8.56	8.8	9.5	10.0	11.0	11.13	12.5		
	in	0.091	0.102	0.109	0.113	0.114	0.126	0.142	0.154	0.157	0.177	0.197	0.217	0.237	0.248	0.280	0.300	0.315	0.337	0.346	0.375	0.394	0.433	0.438	0.492		
OD		Lungime min-max (m)/ Min -Max Length (m)																									
mm	in																										
21.3	0.839	6-12	6-12	6-12	6-12	6-12	6-12	6-12																			
26.7	1.051	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12																		
26.9	1.059	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12																		
28.0	1.102		6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12																	
30.0	1.181		6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12																	
31.8	1.252		6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12																
33.4	1.315		6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12															
33.7	1.327		6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12															
38.0	1.496		6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12														
42.2	1.661		6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12													
42.4	1.669		6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12													
48.3	1.902		6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12												
51.0	2.008		6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12											
54.0	2.126				6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12										
57.0	2.244				6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12										
60.3	2.374				6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12
63.5	2.500				6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12
70.0	2.756				6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12
73.0	2.874				7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13
76.1	2.996				7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13
82.5	3.248						7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13
88.9	3.500						6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12	6-12
95.0	3.740						7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13
101.6	4.000						7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13
108.0	4.252						7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13
114.3	4.500						7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13	7-13
121.0	4.760																										
127.0	5.000																										
134.0	5.276																										
	HP1 Category																										
	HP2 Category																										
	HP3 Category																										
	HP4 Category																										

   Polygonal aspect at ID being within the tolerances (OD/WT<=8). Do not roll from steels with Rm> = 355 N / mm2 (E355, 20MnV6, 42CrMo4, etc)

 This dimensional range can also be applied quenching and tempering